

A-2TiB

Classification

AWS	AWS A5.23 EA2TiB
EN	ISO 14171-A S2MoTiB

Features

- Submerged arc welding wire for standard carbon steel
- Typical applications include pipes

Typical Chemical Composition of the Wire (wt%)

C	Si	Mn	P	S	Mo	Ti	B
0.06	0.25	1.21	0.009	0.002	0.53	0.14	0.012

Wire Diameter & Packaging

Wire Diameter mm(in)	Packaging
4.0 (5/32)	Basket 25kg(55lbs) Coil 25kg(55lbs), 100kg(220lbs), 200kg(440lbs), 250kg(551lbs), 300kg(661lbs), 500kg(1102lbs) Drum 250kg(551lbs), 300kg(661lbs), 350kg(771lbs), 400kg(881lbs)

SAW

SAW

SAW

SAW

Metal-cored Wire

SAW Wire

SAW Flux