H-14L

Classification

AWS	AWS A5.23 EG
JIS	JIS Z 3351 YS-S6
EN	ISO 14171-A SZ

Features

- Submerged arc welding wire for standard carbon steel
- Typical applications include pipes and steel structures

Typical Chemical Composition of the Wire (wt%)

C	Si	Mn	P	S
0.05	0.05	1.98	0.017	0.005

Wire Diameter & Packaging

Packaging
Basket 25kg(55lbs) Coil 25kg(55lbs), 100kg(220lbs), 200kg(440lbs), 250kg(551lbs), 300kg(661lbs), 500kg(1102lbs) Drum 250kg(551lbs), 300kg(661lbs), 350kg(771lbs), 400kg(881lbs)