

S-316L.16N

Classification

AWS A5.4/ASME SFA-5.4 E316L-16
JIS Z 3221 ES316L-16
EN ISO 3581- A E 19 12 3 L R
KS D7014 E316L-16

Welding Positions





Features

- Good resistance to corrosion and oxidizing environments
- Good heat resistance
- Easy to remove slag

Polarity

AC or DC+

Application Areas

- Stainless steel (low carbon 18%Cr-12%Ni-2%Mo)

Redrying Conditions

350°C (662°F) X 1hr

Approvals

ABS	BV	CCS	DNV	KR	LR	NK	CWB	CE	DB	TUV
✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓

Typical Chemical Composition of All-Weld Metal (wt%)

C	Si	Mn	P	S	Cu	Ni	Cr	Mo
0.02	0.75	0.9	0.018	0.012	0.02	12.7	18.5	2.7

Typical Mechanical Properties of All-Weld Metal

Tensile Strength MPa(ksi)	Elongation (%)	Temperature °C (°F)	Impact Toughness J (ft·lbs)
557(81)	45	-20(0) -60(-75)	53(39) 43(32)

Diameter / Welding Parameters / Packaging

Diameter mm(in)	Length mm(in)	F & HF	V-up, OH	Packaging
2.0 (5/64)	300 (12)	25~55	20~50	PVC - Packet 2.5kg(5.5lbs), Carton 10kg (22lbs)
2.6 (3/32)	300 (12)	50~85	45~80	
3.2 (1/8)	350 (14)	70~115	65~110	
4.0 (5/32)	350 (14)	95~145	85~135	
5.0 (3/16)	350 (14)	135~180	-	