SA-08

Classification

AWS AWS A5.14
ERNiMo- 8

Features

- Submerged arc welding wire for welding of 9% Ni steel
- Typical applications 9% Ni LNG storage tanks

Typical Chemical Composition of the Wire (wt%)

C	Si	Mn	P	S	Ni	Cr	Mo	Fe	W
0.01	0.21	0.1	0.004	0.001	68.2	2.1	18.7	5.6	3.1

Wire Diameter & Packaging

Wire Diameter mm(in)	Packaging
2.4 (3/32)	Coil 25kg(55lbs)