
SC-91LT


Classification

AWS AWS A5.29 / ASME SFA-5.29 E91T1-Ni2C-J

EN ISO 17632-A T50 6 Z P C1 2 H5

Welding Positions





Features

- Designed for welding with 100%CO2 shielding gas
- Good impact value at low temperature

Polarity

DC +

Application Areas

- Shipbuilding
- Offshore structure

Shielding Gas

100% CO2

Approvals

ABS	DNV	LR	RS	CWB
✓	✓	✓	✓	✓

Typical Chemical Composition of All-Weld Metal (wt%)

Shielding Gas	C	Si	Mn	P	S	Ni
100% CO2	0.04	0.25	1.25	0.010	0.010	2.30

Typical Mechanical Properties of All-Weld Metal

Shielding Gas	Yield Strength MPa(ksi)	Tensile Strength MPa(ksi)	Elongation (%)	Temperature °C (°F)	Impact Toughness J (ft·lbs)
100% CO2	644 (93)	676 (98)	23	-40 (-40) -60 (-75)	95 (70) 80 (59)

Diameter / Welding Parameters / Packaging

Wire Diameter mm(in)	Current (A)	Packaging
1.2 (0.045)	110~280	Spool 5kg (11lbs), 12.5kg (28lbs), 15kg (33lbs), 20kg (44lbs) Drum 100kg (221lbs), 200kg (441lbs), 250kg (551lbs)