YS-308L

Classification

AWS	AWS A5.9 E308L
JIS	JIS Z 3321 YS308L
EN	ISO 14343-A S 19 9 L

Features

- Submerged arc welding wire for stainless steel
- Typical applications include stainless steel structures

Typical Chemical Composition of the Wire (wt%)

C	Si	Mn	P	S	Ni	Cr
0.02	0.40	1.9	0.01	0.01	10.6	20.0

Wire Diameter & Packaging

Packaging
Coil 25kg(55lbs)