YS-316L

Classification

AWS	AWS A5.9 E316L
JIS	JIS Z 3321 YS316L
EN	ISO 14343-A S 19 12 3 L

Features

- Submerged arc welding wire for stainless steel
- Typical applications include stainless steel structures

Typical Chemical Composition of the Wire (wt%)

C	Si	Mn	P	S	Ni	Cr	Mo
0.02	0.35	1.8	0.01	0.01	13.0	18.5	2.6

Wire Diameter & Packaging

Packaging
Coil 25kg(55lbs)